STRATA GREY OR MOTTLED GREY/BLACK

Description These slates show a medium grey colored background accented by black stripes at different orientations. Moderate weathering to buff and brown tones will appear over the surface of the slate.

Origin Vermont

| Lengths (inches) | Widths (inches) | Exposure (3" Headlap, inches) |
|-------------------------------------|---------------------|-------------------------------|
| 24 | 12, 14 | 10.5 |
| 22 | 11, 12, 14 | 9.5 |
| 20 | 10, 11, 12 | 8.5 |
| 18 | 9, 10, 11, 12 | 7.5 |
| 16 | 8, 9, 10, 11, 12 | 6.5 |
| 14 | 7, 8, 9, 10, 11, 12 | 5.5 |
| 12 | 6, 7, 8, 9, 10, 12 | 4.5 |
| Thickness (inches) | Pounds per Square | |
| Nominal $\frac{1}{4} - \frac{3}{8}$ | 850-950 | |
| $3/8^{-1}/2$ | 1,300-1,400 | |
| $\frac{1}{2} - \frac{3}{4}$ | 1,800-2,100 | |
| 3/4-1 | 2,700-3,000 | |
| $1-1^{1}/_{4}$ | 3,600-4,000 | |

Please note that not all sizes are available in every thickness. Call for availability.

Slate General Properties

- 100% natural product
- Exceptionally durable, 100-year useful life
- Proven historic performance & beauty
- Non-combustible—Class A Fire Resistant
- Resistant to acid rain, ultra-violet light & chemicals
- Withstands freeze/thaw cycles & high temperatures
- Rated Class 3 and Class 4 Hail Impact Resistance $(\frac{3}{4}$ to 2 inch ice balls)

| | This Slate* | ASTM Standards |
|--------------------|-------------|--------------------|
| Breaking Load | 691 pounds | 575 pounds minimum |
| Water Absorption | 0.138% | 0.25% maximum |
| Depth of Softening | 0.0006" | 0.002" maximum |
| ASTM Rating | S1 | |

^{*}As tested by ASTM. Test report available upon request.

